

COPY PAPER BASE

TS 5437-096-00279545-2004

Type: (TS) KO-16, KO-18

Format: upon request (maximum width – 750 mm)

Raw material: pulp (bleached, unbleached)

Application: production of copy paper, base for the production of heat copying paper

Indicator name	KO-16	KO-18	Testing methods
Paper weight with the area of 1m ² , g	16±0,5	18±0,6	GOST 13199
Density, g/cm ³	0,7		GOST 27015
Breakdown force in the machine direction, kgf, no less than	2,0	2,5	GOST 13525.1
Porosity, mL/min, no more than	6,0		GOST 13525.14
Humidity, %, no more than	5,5-8,0		GOST 13525.19