

# QUALITY INDICATORS

## Dielectric Impregnated Paper

ЭИИ - 66Б

GOST 3441-88

	<b>Indicator name</b>	<b>Standard</b>
<b>1</b>	<b>Paper weight with the area of 1m<sup>2</sup>, g</b>	<b>66±2,5</b>
<b>2</b>	<b>Breakdown force, H, no less than</b> <b>in the machine direction</b> <b>in the transverse direction</b>	<b>59</b> <b>29</b>
<b>3</b>	<b>Paper capillary rise for 5 minutes</b> <b>in mm, in the two directions on average</b>	<b>40±4</b>
<b>4</b>	<b>Electric strength, kV/mm, no less than</b>	<b>5,5</b>
<b>5</b>	<b>Ash content,% , no more than</b>	<b>0,8</b>
<b>6</b>	<b>pH of aqueous extract</b>	<b>6,5-8,5</b>
<b>7</b>	<b>Humidity, %, no more than</b>	<b>4,5-7,0</b>