

## WAXED PAPER BASE MATERIAL

GOST 16711-84

**Type:** (GOST) ODP-25 (white), ODP-35 (grey)

**Format:** 750 mm (other formats upon request)

**Raw material:** pulp (bleached, unbleached)

**Application:** ODP-25 is used for automatized and semi-automatized interior packaging of confectionary items, medicaments packaging, lining of boxes. ODP-35 is used for packaging of metalware.

Indicator name	ODP-25	ODP-28	ODP-35	Testing methods
Paper weight with the area of 1m <sup>2</sup> , g	25±1,7	28±1,4	35±1,8	GOST 13199
Density, g/cm <sup>3</sup>	0,52	0,50	0,50	GOST 27015
Breakdown force, kgf, not less than in the machine direction in the transverse direction	21,0	13,0		GOST 13525.1
Relative elongation in the machine direction, %, not less than	0,8			GOST 13525.1
Whiteness, %, not less than	70,0	70,0		GOST 7690

pH of aqueous extract			6,5-8,5	GOST 12523
Mass fraction of chloride ions, %, no more than			0,0055	GOST 20422
Mass fraction of sulfate ions, %, no more than			0,046	GOST 20422
Humidity, %, no more than	6,0-9,0	6,0-9,0	5,0-8,0	GOST 13525.19